

Pigmented cementitious tiles joint filler

Uses

As a grout for dry tile joints in:

- Kitchens
- Bathrooms
- Shower stalls
- Swimming pools

Advantages

- Low cost service life - mould resistant, tropical grade
- Easy to apply - just add water for a thixotropic, non-slump grout
- Can be used in submerged conditions
- Available in a range of attractive colours

Description

Nitotile Grout is a blend of specially selected cements, fillers and synthetic organic polymers. When added to water it readily blends to produce a smooth creamy paste which when set is water and mould resistant. Nitotile Grout is used in conjunction with Nitotile* tile adhesives.

Properties

Typical Properties of mixed material.

Working time at 20°C	: 90 minutes
Working time at 35°C	: 30 minutes
Compressive strength (ASTM C 109)	: 38 N/mm ² @ 28 days
Tensile strength (BS 6319: Pt 7)	: 3 N/mm ² @ 28 days

Instructions for use

Preparation

All tiles must be securely fixed in place and thoroughly cleaned before Nitotile Grout is applied. The gap between tiles should not exceed 4mm. Tile joint filling should only be done 24 hours after fixing the tiles.

Mixing

300 ml of water are required for each kg bag of Nitotile Grout. Add powder to water and mix until a uniform, lump-free, thick creamy paste is produced, allow to stand for ten minutes prior to use.

Application

Apply Nitotile Grout to the spaces between the tiles using a sponge or a small piece of soft cloth. Work the mixture into the joints and around the edges.

Remove surplus material from the face of the tiles with a dry cloth and run the tip of a gloved finger or suitable rounded tool along the grout to level it off and form a profile.

When the grout is dry, clean the tiles with a damp sponge to remove any excess material. It is advisable to remove uncured grout from textured tiles prior to setting, failure to do so may result in difficulty in removal.

Cleaning

Nitotile Grout should be removed from tools, equipment and mixers with clean water immediately after use. Cured material can only be removed mechanically.

Limitations

Nitotile Grout should not be used when the temperature is below 5°C and falling. The product should not be exposed to moving water during application. If any doubts arise concerning temperature or substrate conditions, consult your local Fosroc office.

Estimating

Supply

Nitotile Grout	: 1 kg pack
-----------------------	-------------

Coverage

Nitotile Grout	: Approx. 49 running meter of 3mmx5mm joint / kg.
-----------------------	---

Storage

Shelf life

Nitotile Grout has a shelf life of 12 months if kept in a dry store in the original, unopened bags or packs.

Storage conditions

Store in dry conditions in the original, unopened bags or packs. If stored at high temperature and / or high humidity conditions the shelf life may be reduced.

Technical support

Fosroc offers a comprehensive range of high performance, high quality repair, maintenance and construction products. In addition, Fosroc offers a technical support package to specifiers, end-users and contractors, as well as on-site technical assistance in locations all over the world.

Precautions**Health and safety**

Nitotile Grout is cement based. Care should be taken to avoid inhalation of dust and contact with eyes. All cement based products, when mixed or damp release alkalis which can be harmful to the skin.

Additional Information

Nitotile Grout is part of a range of Fosroc tile adhesives and tile grouts.

Fosroc manufactures a wide range of complementary products which include:

- Waterproofing membranes & waterstops
- Joint sealants & filler boards
- Cementitious & epoxy grouts
- Specialised flooring materials

Fosroc additionally offers a comprehensive package of products specifically designed for the repair and refurbishment of damaged concrete. Fosroc's 'Systematic Approach' to concrete repair features the following:

- Hand-placed repair mortars
- Spray grade repair mortars
- Fluid micro-concretes
- Chemically resistant epoxy mortars
- Anti-carbonation/anti-chloride protective coatings
- Chemical and abrasion resistant coatings

For further information on any of the above, please consult your local Fosroc office - as below.

® Denotes the trademark of Fosroc International Limited

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

**Fosroc Chemicals (India) Pvt. Ltd.****Head Office**

111/3, Hafeeza Chamber II Floor,
K H Road, PBNo. 2744, Bangalore 560027

www.fosroc.com

telephone

++91 80-22240018/120

fax

++91 80-22233474

e-mail

india@fosroc.com

**Regional Offices****Bangalore**

Shankar House, IV Floor
1 & 18, RMV Extension
Bangalore 560 080
Ph:080-2361 3161/2361 2004
Fax : 080-2361 7454
email: Bangalore@fosroc.com

Mumbai

208/209, Persepolis
Sector 17, Vashi
Navi Mumbai 400 703
Ph:022-2789 6412/14
Fax: 022 - 2789 6413
email:Mumbai@fosroc.com

Delhi

First floor, 1/2 East Patel Nagar
Opp: Vivek Cinema, Main Patel Rd
New Delhi 110 008
Ph:011-25884903/4
Fax: 011- 25884422
email:Delhi@fosroc.com

Kolkata

30/B Jodhpur Park
Ground Floor
Kolkata 700 068
Ph: 033 2472 5482
Fax: 033-2472 9921
email:Kolkata@fosroc.com

●Ahmedabad : (079) 26762799 ●Ankleshwar : (02646) 220704/224687 ●Bhubaneswar : (0674) 2521176 ●Chennai (044) 24899949/24853383
●Chandigarh : (0172) 2639360 ●Cochin : (0484) 2356668 ●Coimbatore : (0422) 2472966 ●Goa : (0832) 2542465 ●Guwahati (0361) 2548793
●Hyderabad : (040) 27662324/27662425 ●Hubli (0836) 3402597 ●Indore : (0731) 504339/5061477 ●Jaipur : (0141) 2235349 ●Lucknow : (0522)
22239044 ●Nagercoil (04652) 2224849 ●Mangalore: (0824) 22272234 ●Visakhapatnam : (0891) 2564850